

Title: Experimental signatures of phase competition in quantum XY pyrochlores


Date: Jun 07, 2017 02:50 PM

URL: <http://pirsa.org/17060036>

Abstract: The erbium and ytterbium rare earth pyrochlores exhibit local XY spin anisotropy. Experimental and theoretical investigations of XY pyrochlores have revealed a strong propensity for quantum magnetic phenomena, such as order-by-disorder and the quantum spin ice state. We have conducted a systematic investigation of the family of XY pyrochlores, $\text{Yb}_2\text{B}_2\text{O}_7$ and $\text{Er}_2\text{B}_2\text{O}_7$, spanning many non-magnetic B site cations ($\text{B} = \text{Ge}, \text{Ti}, \text{Pt}, \text{and Sn}$). We have characterized the magnetism of these XY pyrochlores using heat capacity, muon spin relaxation, neutron diffraction, and inelastic neutron scattering. A diversity of magnetic ground states and behaviours are represented among this family, ordered states ranging from ferromagnetic to antiferromagnetic, and in the case of one material, an absence of magnetic order to at least 100 mK. Moreover, we find that the magnetic ground state properties of these materials are strongly influenced by proximity to competing magnetic phases, consistent with theoretical predictions. We empirically demonstrate the signatures for phase competition in the frustrated XY pyrochlores: multiple heat capacity anomalies, suppressed TN or Tc, sample and pressure dependent ground states, and unconventional spin dynamics.

Experimental Signatures of Phase Competition in Quantum XY Pyrochlores

Alannah Hallas
McMaster University



XY Pyrochlore Collaborators



McMaster
University (Canada)

Alannah Hallas

Bruce Gaulin

Graeme Luke

Jonathan Gaudet

Murray Wilson

Yipeng Cai

National Institute for
Materials Science (Japan)

Makoto Tachibana



University of
Edinburgh (UK)

Paul Attfield

Angel Arevalo-Lopez



NIST Center for
Neutron Research (USA)

Nick Butch

Guangyong Xu



University of
Winnipeg (Canada)

Chris Wiebe

Arzoo Sharma

Universidade de
Sao Paulo (Brazil)

Rafael Freitas


ORNL (USA)

Adam Aczel

Matt Stone



Theoretical work on phase competition in the XY pyrochlores



PRL 115, 267208 (2015)

PHYSICAL REVIEW LETTERS

week ending
31 DECEMBER 2015

Are Multiphase Competition and Order by Disorder the Keys to Understanding $\text{Yb}_2\text{Ti}_2\text{O}_7$?

L. D. C. Jaubert,¹ Owen Benton,¹ Jeffrey G. Rau,² J. Oitmaa,³ R. R. P. Singh,⁴ Nic Shannon,¹ and Michel J. P. Gingras^{2,5,6}

¹Okinawa Institute of Science and Technology Graduate University, Onna-son, Okinawa 904-0495, Japan

²Department of Physics and Astronomy, University of Waterloo, 200 University Avenue West, Waterloo, Ontario N2L 3G1, Canada

³School of Physics, The University of New South Wales, Sydney 2052, Australia

⁴Department of Physics, University of California, Davis, California 95616, USA

⁵Perimeter Institute for Theoretical Physics, 31 Caroline North, Waterloo, Ontario N2L 2Y5, Canada

⁶Canadian Institute for Advanced Research, Toronto, Ontario M5G 1Z8, Canada

(Received 20 May 2015; revised manuscript received 12 September 2015; published 29 December 2015)

PHYSICAL REVIEW B 95, 094422 (2017)

Theory of multiple-phase competition in pyrochlore magnets with anisotropic exchange with application to $\text{Yb}_2\text{Ti}_2\text{O}_7$, $\text{Er}_2\text{Ti}_2\text{O}_7$, and $\text{Er}_2\text{Sn}_2\text{O}_7$

Han Yan,^{1,2} Owen Benton,^{1,3} Ludovic Jaubert,^{1,4} and Nic Shannon^{1,2,3}

¹Okinawa Institute of Science and Technology Graduate University, Onna-son, Okinawa 904-0395, Japan


²Clarendon Laboratory, University of Oxford, Parks Rd., Oxford OX1 3PU, United Kingdom

³H. H. Wills Physics Laboratory, University of Bristol, Tyndall Av, Bristol BS8-1TL, United Kingdom

⁴Rudolf Peierls Centre for Theoretical Physics, University of Oxford, 1-6 Keeble Rd, Oxford OX1 3NP, United Kingdom




(Received 20 December 2013; revised manuscript received 21 February 2017; published 17 March 2017)

Many of the experimentally observed properties of the XY pyrochlores can be accounted for by a model of phase competition






- Several different magnetic ground states obtained within a narrow range of exchange parameters (via chemical pressure) (*this talk*)
- Suppressed ordering transition, T_N or T_C (*this talk*)
- Sensitivity to disorder (*e.g. talk of Tyrel McQueen*) and sensitivity to applied pressure (*e.g. Kermarrec et al., Nature Comm. 2017*)

Sensitivity to externally applied pressure in $\text{Yb}_2\text{Ti}_2\text{O}_7$




Kermarrec, Gaudet, Gaulin et al., Nature Comm. 8 14810 (2017).

Sensitivity to externally applied pressure in $\text{Yb}_2\text{Ti}_2\text{O}_7$





Kermarrec, Gaudet, Gaulin et al., *Nature Comm.* 8 14810 (2017).

This talk will examine the effect of chemical pressure on the ground states of the XY pyrochlores.





H	(Yb ³⁺) ₂ (B ⁴⁺) ₂ O ₇ & (Er ³⁺) ₂ (B ⁴⁺) ₂ O ₇																He
Li	Be	Yb ³⁺ : [Xe] 4f ¹³ , $J = 7/2$ Er ³⁺ : [Xe] 4f ¹¹ , $J = 15/2$										B	C	N	O	F	Ne
Na	Mg											Al				P	S
K	Ca		Ti				Fe	Co	Ni	Cu	Zn	Ga	Ge	As	Se	Br	Kr
Rb	Sr			Nb						Ag	Cd	In	Sn	Sb	Te	I	Xe
Cs	Ba			Ta	W	Re			Pt	Au	Hg				Po	At	Rn




										Er		Yb	
Th	Pa	U	Np	Pu	Am	Cm	Bk	Cf	Es	Fm	Md	No	Lr



Each of the $\text{Er}_2\text{B}_2\text{O}_7$ and $\text{Yb}_2\text{B}_2\text{O}_7$ ($\text{B} = \text{Ge}, \text{Ti}, \text{Pt}, \text{Sn}$) pyrochlores has local XY spin anisotropy



$$g_{\perp} = 6.3 \quad g_z = 3.9$$






$\text{Yb}_2\text{Ti}_2\text{O}_7$: Gaudet et al., PRB 92, 134420 (2015).

$\text{Yb}_2\text{Ge}_2\text{O}_7$: Hallas et al., PRB 93, 104405 (2016)



$\text{Er}_2\text{B}_2\text{O}_7$: Gaudet et al., in preparation

Four classical states in the anisotropic exchange phase diagram for XY pyrochlores.




Yan, Benton, Jaubert and Shannon, PRB 95 094422 (2017).

We have investigated the low temperature magnetism of two new members of the XY pyrochlore family.





Hallas, Gaudet, Gaulin, to appear in Annual Reviews of Condensed Matter Physics

The Yb pyrochlores share a common form for their specific heat.








Hallas, Gaudet, Gaulin, to appear in Annual Reviews of Condensed Matter Physics

Positive chemical pressure takes $\text{Yb}_2\text{B}_2\text{O}_7$ from Γ_9 ferromagnet to Γ_5 antiferromagnet (ψ_2 or ψ_3).



Hallas et al., PRB 93, 104405 (2016)


The spin excitations of $\text{Yb}_2\text{Ge}_2\text{O}_7$ do not evolve below $T_N = 0.6$ K.




Hallas et al., PRB 93, 100403(R) (2016).

The low temperature spin excitations of the ytterbium pyrochlores share a ubiquitous form.

Gapless Continuum of Excitations





Spin Waves




Hallas et al., PRB 93, 100403(R) (2016).

We have investigated the low temperature magnetism of two new members of the XY pyrochlore family.




Hallas, Gaudet, Gaulin, to appear in Annual Reviews of Condensed Matter Physics


Negligible chemical pressure takes $\text{Er}_2\text{B}_2\text{O}_7$ from ψ_2 antiferromagnet to Γ_7 Palmer Chalker antiferromagnet.





Hallas et al., arXiv 1705.06680 (2017)



Short range correlations develop in $\text{Er}_2\text{Pt}_2\text{O}_7$ at $T^* = 1.5$ K.





Hallas et al., arXiv 1705.06680 (2017)



$\text{Er}_2\text{Ti}_2\text{O}_7$ &
 $\text{Er}_2\text{Ge}_2\text{O}_7$

$\text{Yb}_2\text{B}_2\text{O}_7$, $\text{Er}_2\text{Pt}_2\text{O}_7$,
& $\text{Er}_2\text{Sn}_2\text{O}_7$




$\text{Er}_2\text{Ti}_2\text{O}_7$ & $\text{Er}_2\text{Ge}_2\text{O}_7$

- Order above 1 K
- Single sharp heat capacity anomaly
- No known sensitivity to disorder

$\text{Yb}_2\text{B}_2\text{O}_7$, $\text{Er}_2\text{Pt}_2\text{O}_7$, & $\text{Er}_2\text{Sn}_2\text{O}_7$

- Order well below 1 K
- Two stage entropy release
- Strong sensitivity to disorder ($\text{Yb}_2\text{Ti}_2\text{O}_7$)

Many of the experimentally observed properties of the XY pyrochlores can be accounted for by a model of phase competition



- Several different magnetic ground states obtained within a narrow range of exchange parameters (via chemical pressure) (*this talk*)
- Suppressed ordering transition, T_N or T_C (*this talk*)
- Sensitivity to disorder (*e.g. talk of Tyrel McQueen*) and sensitivity to applied pressure (*e.g. Kermarrec et al., Nature Comm. 2017*)
- Multiple heat capacity anomalies and unconventional spin dynamics (*this talk and talk of Radu Coldea*)